



Certificate
of
Analysis

Product #

10-501

Premier Finishes, Inc.

Red Iron Oxide Basecoat MDF Primer

PHYSICAL CHARACTERISTICS

Weight per gallon:	12.72
% Solids by weight:	60.03
% Solids by volume:	38.96
PH:	8.3 – 9.3
Viscosity:	126 – 130 KU
Flash Point (closed cup):	None
Spread Rate:	625 sq. ft. @ 1 mil
Material VOC:	0.00 lb. / gal.
Coatings VOC (-water):	0.00 lb. / gal.

Application Specifications

Method: Product can be applied by airless or assisted-airless spray or vacuum coater.

Reduction: Water, if necessary.

Special Notes

Please read the SDS before using this product.

Shelf life: Six months – please rotate stock on a regular basis. Do not freeze. Product will not recover.

Regulatory status: This product is not considered a hazardous waste under current RCRA regulations. This product does not contain, nor is it manufactured using ozone depleting substances as listed under Section 611 of the Clean Air Act.

PremierFinishes.net